



New Water Range Recommendations for Schluter Thin-Sets




Water ranges by application type	SET		ALL-SET	
	OLD	NEW	OLD	NEW
Tile	5.5 - 6.5 qts (5.2 - 6.2 L)	5.3 - 6.0 qts (5.0 - 5.7 L)	5.5 - 6.5 qts (5.2 - 6.2 L)	5.1 - 5.8 qts (4.8 - 5.5 L)
Membrane	7.5 - 8.5 qts (7.1 - 8.0 L)	6.2 - 7.2 qts (5.9 - 6.8 L)	7.5 - 8.5 qts (7.1 - 8.0 L)	6.0 - 7.0 qts (5.7 - 6.6 L)



A New Greener Formula!

In line with our commitment to sustainability, our thin-set formulas now incorporate Portland Limestone Cement (PLC). By replacing a portion of Ordinary Portland Cement with limestone during the grinding process, we can reduce carbon dioxide emissions and promote a more sustainable manufacturing process, all while maintaining comparable final strength—aligning with industry-wide initiatives for a greener construction sector.



It is important to read the thin-set bag before use as old material may still be in circulation.

For suitable uses, coverage information, and mixing instructions,

[SCAN HERE](#)

